

BONDERITE C-AK 6849 AERO

AQUEOUS ALKALINE DEGREASER

(KNOWN AS TURCO 6849)

INTRODUCTION:

BONDERITE C-AK 6849 AERO (known as TURCO 6849) is a clear aqueous alkaline degreaser formulated to remove shop soils, marking inks, cosmoline, grease and lube oils from ferrous and non-ferrous alloys. BONDERITE C-AK 6849 AERO offers both exceptional effectiveness and exceptional tank life.

BONDERITE C-AK 6849 AERO replaces solvent type vapor degreasing fluids with an effective aqueous cleaner. The costs and hazards normally associated with chlorinated solvent cleaning are thereby greatly reduced.

An additive is available to help provide exceptional cleaning on even the most difficult oily soils.

FEATURES:

- Approved to Boeing BAC 5763, Type 2
- Exceptional tank life
- Low VOC content (28 g/l)
- Passes titanium stress corrosion test per ASTM F-945
- Passes intergranular attack per BSS 7219
- Does not contain chromate or chlorides
- Passes hydrogen embrittlement test per ASTM F-519, Type 1C (10% and neat)
- Noncorrosive to aluminum, steel, copper, titanium, stainless steel, plated metals and magnesium alloys (BAC 5763, 12.2.1.)
- Passes sandwich corrosion per Boeing D6-17487

USE INSTRUCTIONS:

Tanks: Tanks and associated equipment may be fabricated from mild steel or stainless steel.

Add BONDERITE C-AK 6849 AERO at 10 to 20% by volume to water, for immersion. Operate solution from 55° to 70°C, with air or mechanical agitation.

Rinsing: Rinse with hot or cold water. Warm water is preferred.



BONDERITE C-AK 6849 AERO

AQUEOUS ALKALINE DEGREASER

(KNOWN AS TURCO 6849)

CONTROL:**Apparatus:**

1. pH Meter
2. 205402 - Beaker, 250 mL
3. 205945 - Pipet, 25 mL
4. 205700 - Buret, 25 ML

Reagents:

1. 205220 - Titrating Solution 20 (0.1N Sulfuric Acid)
2. 205002 - Indicator 2 (Bromocresol Green)

Procedure:

1. Obtain a sample from the tank and cool to room temperature.
2. Pipet 25 mL sample into a 250 mL beaker containing 50 ml DI water.
3. Titrate with TS 20 to pH 4.
4. If pH meter is not available add 5-8 drops of Indicator 2. Titrate with TS 20 until the color of the solution changes from blue green to yellow.

Calculation:

mLs of TS 20 X 0.63 = % BONDERITE C-AK 6849 AERO (using Indicator 2)
mLs of TS 20 X 0.55 = % BONDERITE C-AK 6849 AERO (using pH meter)

Maintenance:

Maintain bath concentration within recommended range by adding fresh materials

Recommended Concentration: 10 -20%

Laboratory experience indicates that BONDERITE C-AK 6849 AERO has a high capacity for soils. The time between recharging will vary and is dependent upon the work and the amount of soil removed.

DISPOSAL INFORMATION:

Dispose of spent solution per local, state and regional regulations. Refer to your HENKEL SURFACE TECHNOLOGIES MATERIAL SAFETY DATA SHEET for additional disposal information.



BONDERITE C-AK 6849 AERO AQUEOUS ALKALINE DEGREASER (KNOWN AS TURCO 6849)

PRECAUTIONARY INFORMATION:

BONDERITE C-AK 6849 AERO is considered to be a relatively nonhazardous industrial cleaner. However, as in the case of any chemical compound, avoid contact with eyes, skin and clothing. Do not take internally. Use with adequate (equivalent to outdoor) ventilation.

Protective clothing such as a chemical face shield or goggles and gloves, boots and apron made from alkali-resistant materials, should be worn by using personnel. A **NIOSH approved** respirator equipped with a mechanical filter should be worn during mist conditions.

Store in closed containers away from excessive heat or direct sunlight.

Before using this product refer to container label and HENKEL SURFACE TECHNOLOGIES MATERIAL SAFETY DATA SHEET for additional precautionary, handling and first aid information.

NOTICE:

The above information and recommendations concerning this product are based upon our laboratory tests and field use experience with this or similar products. However, since conditions of actual use are beyond our control, any recommendations or suggestions are made without warranty, express or implied. Manufacturer's and seller's sole obligation shall be to replace that portion of the product shown to be defective. Neither shall be liable for any loss, damage, or injury, direct or consequential, arising out of the use of this product.

Rev. 8/2013

Henkel Corporation | 32100 Stephenson Highway | Madison Heights, MI 48071
PHONE: (248) 583-9300 | FAX: (248) 583-2976 | www.henkelna.com/

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.**

The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

